

The application was originally made under the Patent Cooperation Treaty with the United States of America Patent Office acting as the Receiving Office on (86) 19 July 1982, being given an application number PCT/US82/00976. The application was searched by the United States of America Patent Office acting as the International Search Authority (ISA), and published by the International Bureau on (87) 2 February 1984 under serial number WO 84/00385 in the English language. The text of the application is contained in the publication made by the International Bureau as above identified.

(12) UK Patent Application (19) GB (11) 2 134 542 A

(21) Application No 8406512
(22) Date of filing 19 July 1982
(43) Date of issue
15 Aug 1984

(51) INT CL³ (as given by ISA)
C22C 37/08

(52) Domestic classification
C7A A249 A250 A253
A255 A257 A259 A25Y
A260 A263 A266 A269
A272 A276 A279 A27X
A28X A28Y A300 A303
A305 A307 A309 A30Y
A311 A313 A316 A319
A31X A320 A323 A326
A329 A330 A337 A339
A33Y A340 A341 A343
A345 A347 A349 A34Y
A350 A352 A354 A356
A358 A35Y A360 A362
A364 A366 A369 A36Y
A370 A375 A377 A379
A37Y A381 A383 A385
A387 A389 A38X A390
A394 A396 A398 A39Y
A400 A402 A404 A406
A409 A40Y A439 A459
A509 A514 A517 A519
A51X A51Y A521 A523
A525 A527 A52X A53X
A53Y A551 A553 A555
A557 A559 A55X A55Y
A562 A565 A568 A56X
A571 A574 A577 A579
A57Y A599 A609 A629
A671 A673 A675 A677
A679 A67X A681 A683
A685 A687 A689 A68X
A693 A695 A697 A699
A69X A70X
U1S 1613 2003 3035
3042 C7A

(56) Documents cited by ISA
JP 56-93859 A
SU 618444 A
SU 729273 A
JP 47-4791 B
US 4221612 A
NL 6917161 A
US 2978320 A

(58) Field of search by ISA
US 75/123CB
126A
126P
128D
128F
148/35
138

(71) Applicants
GIW Industries Inc.,
(USA-Georgia),
5000 Wrightsboro Road,
Grovettown,
Georgia 30813,
United States of America

(72) Inventor
Wallace Day

(74) Agent and/or
Address for Service
Withers & Rogers,
4 Dyer's Buildings,
Holborn,
London EC1N 2JT

(54) Abrasive resistant white cast iron

(57) A white cast iron having toughness, high tensile strength and abrasion resistance containing 0.1% to 4.0% boron in an iron-carbon alloy with the carbides in the form of globules and of an average size less than 4 microns. This white cast iron is produced by incorporating the boron in the composition to form a melt, super cooling the melt while liquid to at least 5°F below the equilibrium solidification temperature between 2200°F to 2400°F and then solidifying the melt to produce the globules of carbides uniformly dispersed and having a size much smaller than the size of the carbide particles of conventional cast iron.